



TEST REPORT



98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5380

FAX 82-31-499-6867

Report No : TAK-2024-160036

Receipt Date : 2024.11.08.

Representative : Se-Hong, Min, Yeong-Seok, Yang, Woo-Jin, Kim

Test Completion Date : 2025.01.13.

Company name : DONGIL-STEEL MFG.Co.,Ltd

Address : #1F-1ho, 474-40, Anseongmatchum-Daero, Miyang-Myeon, Anseong-si, Gyeonggi-do, Korea

Sample name : PC Prestressing strand(SWPC7BL 7/12.7mm)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD	SITE
Relaxation (1 000 h)	%	-	1.8	KS D 7002 : 2019	AK

- Refer to relaxation test data sheet

- AK: 98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

- Usage of Report : QUALITY CONTROL

- Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

The above testing certificate is the accredited test result by Korea Laboratory Accreditation Scheme, which signed the ILAC-MRA.

Kim Taek-gyun

Prepared by Kim Taek-gyun

Tel : 02-2092-3633

Oh Donghyun

Reviewed by Oh Donghyun

Tel : 1577-0091(ARS ①→④)

2025.01.13

Korea Testing & Research Institute

Accredited by KOLAS, Republic of KOREA

President Kim Hyun cheol



QR Code for forgery

RELAXATION TEST

▶ Report NO. : TAK-2024-160036

▶ Sample Name : PC강연선(SWPC7BL 7/12.7mm)
PC Prestressing strand(SWPC7BL 7/12.7mm)

▶ Test Method : KS D 7002:2019

▶ Test Result ;

-Test Item : Relaxation (1 000 h)

-Initial Load : 128.49 (kN)

-Final Load : 126.13 (kN)

-Initial Reading of Temperature : 20(℃)


-Final Reading of Temperature : 21(℃)

TIME (h)	LOAD (kN)	RELAXATION RATE (%)	TIME (h)	LOAD (kN)	RELAXATION RATE (%)
1	127.37	0.87	110	126.62	1.46
2	127.28	0.94	120	126.62	1.46
3	127.21	1.00	130	126.59	1.48
4	127.15	1.05	140	126.59	1.48
5	127.11	1.07	150	126.55	1.51
6	127.08	1.10	160	126.55	1.51
7	127.08	1.10	170	126.52	1.53
8	127.05	1.12	180	126.52	1.53
9	127.05	1.12	190	126.52	1.53
10	127.01	1.15	200	126.49	1.56
20	126.92	1.23	300	126.46	1.58
30	126.82	1.30	400	126.36	1.66
40	126.78	1.33	500	126.32	1.69
50	126.75	1.35	600	126.29	1.71
60	126.72	1.38	700	126.29	1.71
70	126.69	1.40	800	126.19	1.79
80	126.65	1.43	900	126.13	1.84
90	126.65	1.43	1000	126.13	1.84
100	126.62	1.46			

RELAXATION TEST

- ▶ Report NO. : TAK-2024-160036
- ▶ Sample Name : PC강연선(SWPC7BL 7/12.7mm)
PC Prestressing strand(SWPC7BL 7/12.7mm)
- ▶ Test Method : KS D 7002:2019

< Relaxation Curve >



▶ RELAXATION RATE (Test Time : 1 000 hours):

- Initial Load : Minimum Breaking Strength $\times$ 70(%) = 128.49 (kN)
- Final Load : 126.13 (kN)

▶ RELAXATION RATE(%) = $\frac{\text{Initial Load} - \text{Final Load}}{\text{Initial Load}} \times 100 (\%) = 1.8(\%)$