



TEST REPORT



98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5380

FAX 82-31-499-6867

Report No : TAK-2025-070999

Receipt Date : 2025.05.15.

Representative : Se-Hong, Min, Yeong-Seok, Yang, Woo-Jin, Kim

Test Completion Date : 2025.07.17.

Company name : DONGIL-STEEL MFG.Co.,Ltd

Address : #1F-1ho, 474-40, Anseongmatchum-Daero, Miyang-Myeon, Anseong-si, Gyeonggi-do, Korea

Sample name : PC Prestressing strand [heteromorphic 3 line 2.9mm(SWPD3L)]

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD	SITE
Relaxation (1 000 h)	%	-	2.1	KS D 7002 : 2019	AK

- Refer to relaxation test data sheet

- AK: 98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

- Usage of Report : QUALITY CONTROL

- End of Report -

- Note :
1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
 3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

The above testing certificate is the accredited test result by Korea Laboratory Accreditation Scheme, which signed the ILAC-MRA.

Kim Taek-gyun

Prepared by Kim Taek-gyun

Tel : 02-2092-3633

Oh Donghyun

Reviewed by Oh Donghyun

Tel : 1577-0091(ARS ①→④)

2025.07.17

Korea Testing & Research Institute

Accredited by KOLAS, Republic of KOREA

President *Kim Hyun cheol*




QR Code for forgery

RELAXATION TEST

- ▶ Report NO. : TAK-2025-070999
- ▶ Sample Name : PC강연선 (이형 3연선 2.9mm(SWPD3L))
PC Prestressing strand [heteromorphic 3 line 2.9mm(SWPD3L)]
- ▶ Test Method : KS D 7002:2019

< Relaxation Curve >



▶ RELAXATION RATE (Test Time : 1 000 hours):

- Initial Load : Minimun Breaking Strength × 70(%) = 26.68 (kN)
- Final Load : 26.12 (kN)

▶ RELAXATION RATE(%) = $\frac{\text{Initial Load} - \text{Final Load}}{\text{Initial Load}} \times 100 (\%) = 2.1(\%)$

RELAXATION TEST

- ▶ Report NO. : TAK-2025-070999
- ▶ Sample Name : PC강연선 (이형 3연선 2.9mm(SWPD3L))
PC Prestressing strand [heteromorphic 3 line 2.9mm(SWPD3L)]
- ▶ Test Method : KS D 7002:2019
- ▶ Test Result ;

-Test Item : Relaxation (1 000 h)
-Initial Load : 26.68 (kN)
-Final Load : 26.12 (kN)
-Initial Reading of Temperature : 21(°C)
-Final Reading of Temperature : 21(°C)

TIME (h)	LOAD (kN)	RELAXATION RATE (%)	TIME (h)	LOAD (kN)	RELAXATION RATE (%)
1	26.45	0.86	110	26.25	1.59
2	26.41	0.98	120	26.25	1.59
3	26.41	0.98	130	26.25	1.59
4	26.38	1.10	140	26.25	1.59
5	26.38	1.10	150	26.25	1.59
6	26.38	1.10	160	26.25	1.59
7	26.38	1.10	170	26.25	1.59
8	26.38	1.10	180	26.25	1.59
9	26.38	1.10	190	26.22	1.72
10	26.38	1.10	200	26.22	1.72
20	26.35	1.23	300	26.22	1.72
30	26.32	1.35	400	26.18	1.84
40	26.32	1.35	500	26.18	1.84
50	26.28	1.47	600	26.15	1.96
60	26.28	1.47	700	26.15	1.96
70	26.28	1.47	800	26.15	1.96
80	26.28	1.47	900	26.12	2.08
90	26.28	1.47	1000	26.12	2.08
100	26.28	1.47			